

# CONTINEX™ N220

## PRODUCT DATA SHEET

Primary Analytical Test Properties:	Target Value	ASTM STM*
Iodine Absorption Number, g/Kg	121	D1510
Oil Absorption No. [OAN] cm <sup>3</sup> /100g	114	D2414

Secondary Physical Test Properties:	Typical Value	
Tint Strength, %	116	D3265
Pour Density, lb/ft <sup>3</sup>	22.0	D1513
Fines Content, % Bulk shipments Bag shipments	3.0 5.0	D1508
Sieve Residue, ppm No. 325 mesh No. 35 mesh	<300 0	D1514
Heating Loss, % Bulk shipments Bag shipments	1.0 1.0	D1509

\* Annual Book of ASTM Standards, Vol. 09.01