



## CONTINEX™ N234

PRODUCT DATA SHEET

Primary Analytical Test Properties:	Target Value	<u>ASTM STM*</u>
Iodine Absorption Number, g / Kg	120	D1510
Oil Absorption No. [OAN] cm <sup>3</sup> / 100g	125	D2414

Secondary Physical Test Properties:	Typical Value	
Tint Strength, %	123	D3265
Pour Density, lb/ft <sup>3</sup>	20.5	D1513
Fines Content, % Bulk shipments	3.0	D1508
Bag shipments	5.0	
Sieve Residue, ppm No. 325 mesh	<300	D1514
No. 35 mesh	0	
Heating Loss, % Bulk shipments	1.0	D1509
Bag shipments	1.0	

\* Annual Book of ASTM Standards, Vol. 09.01