



CONTINEX™ N339

PRODUCT DATA SHEET

Primary Analytical Test Properties:	Target Value	ASTM STM*
Iodine Absorption Number, g / Kg	90	D1510
Oil Absorption No. [OAN] cm ³ / 100g	120	D2414

Secondary Physical Test Properties:	Descriptive Value	ASTM STM*
Tint Strength, %	111	D3265
Pour Density, lb/ft ³	21.5	D1513
Fines Content, % Bulk shipments	5.0	D1508
Bag shipments	10.0	
Sieve Residue, ppm No. 325 mesh	1000 max	D1514
Heating Loss, % Bulk shipments	1.5 max	D1509
Bag shipments	1.5 max	

* Annual Book of ASTM Standards, Vol. 09.01