



CONTINEX™ N660

PRODUCT DATA SHEET

Primary Analytical Test Properties:	Target Value	ASTM STM*
Iodine Absorption Number, g/Kg	36	D1510
Oil Absorption No. [OAN] cm ³ / 100g	90	D2414

Secondary Physical Test Properties:	Descriptive Value	
Pour Density, lb/ft ³	26.5	D1513
Fines Content, % Bulk shipments Bag shipments	5.0 10.0	D1508
Sieve Residue, ppm No. 325 mesh	1000 max	D1514
Heating Loss, % Bulk shipments Bag shipments	1.5 max 1.5 max	D1509

* Annual Book of ASTM Standards, Vol. 09.01