



## SATIN BLACK™ SBX152

### PRODUCT DATA SHEET

Primary Analytical Test Properties:	Target Value	ASTM STM*
Iodine Absorption Number, g/Kg	82	D1510
Oil Absorption No. [OAN] cm <sup>3</sup> /100g	102	D2414

Secondary Physical Test Properties:	Descriptive Value	ASTM STM*
Pour Density, lb/ft <sup>3</sup>	23.5	D1513
Fines Content, % Bulk shipments	5.0	D1508
Bag shipments	10.0	
Sieve Residue, ppm No. 325 mesh	≤ 50	D1514
No. 35 mesh	0	
Heating Loss, % Bulk shipments	1.0	D1509
Bag shipments	1.0	
Pellet Hardness High	60 Max	D5230
Average	30 Max	

\*Annual Book of ASTM Standards, Vol. 09.01