



## CONTINEX™ N120

PRODUCT DATA SHEET

Primary Analytical Test Properties:	Target Value	Recommended Specification	ASTM STM*
Iodine Absorption Number, g/kg	122	116/128	D1510
Oil Absorption No. [OAN] cm <sup>3</sup> / 100g	114	108/120	D2414
Tint Strength, %	129	123/135	D3265

Secondary Physical Test Properties:	Typical Value		
Pour Density, lb/ft <sup>3</sup>	21.5	19.5/23.5	D1513
Fines Content, % Bulk shipments	3.0	/6.0	D1508
Bag shipments	5.0	/9.0	
Sieve Residue, ppm No. 325 mesh	300	/200	D1514
No. 35 mesh	0	/5	
Heating Loss, % Bulk shipments	1.0	/1.5	D1509
Bag shipments	1.0	/2.0	

\*Annual Book of ASTM Standards, Vol. 09.01