



CONTINEX™ N326

PRODUCT DATA SHEET

Primary Analytical Test Properties:	Target Value	Recommended Specification	ASTM STM*
Iodine Absorption Number, g/kg	82	76/88	D1510
Oil Absorption No. [OAN] cm ³ / 100g	72	66/78	D2414
Tint Strength, %	111	105/117	D3265

Secondary Physical Test Properties:	Typical Value		
Pour Density, lb/ft ³	29.0	27.0/30.0	D1513
Fines Content, % Bulk shipments Bag shipments	4.0 6.0	/7.0 /10.0	D1508
Sieve Residue, ppm No. 325 mesh No. 35 mesh	300 0	/200 /5	D1514
Heating Loss, % Bulk shipments Bag shipments	1.0 1.0	/1.5 /2.0	D1509

*Annual Book of ASTM Standards, Vol. 09.01