



CONTINEX™ N339

PRODUCT DATA SHEET

Primary Analytical Test Properties:	Target Value	Recommended Specification	ASTM STM*
Iodine Absorption Number, g/kg	90	84/96	D1510
Oil Absorption No. [OAN] cm ³ /100g	120	114/126	D2414
Tint Strength, %	111	105/117	D3265

Secondary Physical Test Properties:	Typical Value		
Pour Density, lb/ft ³	21.5	19.5/23.5	D1513
Fines Content, % Bulk shipments	3.0	/6.0	D1508
Bag shipments	5.0	/9.0	
Sieve Residue, ppm No. 325 mesh	300	/200	D1514
No. 35 mesh	0	/5	
Heating Loss, % Bulk shipments	1.0	/1.5	D1509
Bag shipments	1.0	/2.0	

*Annual Book of ASTM Standards, Vol. 09.01