



## CONTINEX™ N762

### PRODUCT DATA SHEET

Primary Analytical Test Properties:	Target Value	Recommended Specification	ASTM STM*
Iodine Absorption Number, g/kg	27	21/33	D1510
Oil Absorption No. [OAN] cm <sup>3</sup> / 100g	65	57/71	D2414
Tint Strength, %	57	50/64	D3265

Secondary Physical Test Properties:	Typical Value		
Pour Density, lb/ft <sup>3</sup>	30.45	28.5/32.5	D1513
Fines Content, % Bulk shipments Bag shipments	3.0 5.0	/6.0 /9.0	D1508
Sieve Residue, ppm No. 325 mesh No. 35 mesh	300 0	/200 /5	D1514
Heat Loss, % Bulk shipments Bag shipments	1.0 1.0	/1.5 /2.0	D1509

\*Annual Book of ASTM Standards, Vol. 09.01