



SATIN BLACK™ SBX152

PRODUCT DATA SHEET

Primary Analytical Test Properties:	Target Value	Recommended Specification	ASTM STM*
Iodine Absorption Number, g/kg	82	76/88	D1510
Oil Absorption No. [OAN] cm ³ /100g	102	96/108	D2414
Tint Strength, %	104	98/110	D3265

Secondary Physical Test Properties:	Typical Value		
Pour Density, lb/ft ³	23.5	22/25	D1513
Fines Content, % Bulk shipments	3.0	/6.0	D1508
Bag shipments	5.0	/9.0	
Sieve Residue, ppm No. 325 mesh	≤ 50	/50	D1514
No. 35 mesh	0	0	
Heating Loss, % Bulk shipments	1.0	/1.5	D1509
Bag shipments	1.0	/2.0	
Pellet Hardness, gm High	54	/73	D5230
Average	34	/53	

* Annual Book of ASTM Standards, Vol. 09.01