



SATIN BLACK™ SBX452

PRODUCT DATA SHEET

Primary Analytical Test Properties:	Target Value	Recommended Specification	ASTM STM*
Iodine Absorption Number, g/kg	36	33/99	D1510
Oil Absorption No. [OAN] cm ³ /100g	90	86/94	D2414
Tint Strength, %	57	53/65	D3265

Secondary Physical Test Properties:	Typical Value		
Pour Density, lb/ft ³	26.5	25/28	D1513
Fines Content, %			D1508
Bulk shipments	3.0	/5.0	
Bag shipments	5.0	/7.0	
Sieve Residue, ppm			D1514
No. 325 mesh	≤ 50	/200	
No. 35 mesh	0	0	
Heating Loss, %			D1509
Bulk shipments	1.0	/1.5	
Bag shipments	1.0	/2.0	
Pellet Hardness, gm			D5230
High	54	/65	
Average	34	/45	

*Annual Book of ASTM Standards, Vol. 09.01