



SATIN BLACK™ SBX552

PRODUCT DATA SHEET

Primary Analytical Test Properties:	Target Value	ASTM STM*
Iodine Absorption Number, g/Kg	27	D1510
Oil Absorption No. [OAN] cm ³ /100g	65	D2414

Secondary Physical Test Properties:	Descriptive Value	ASTM STM*
Pour Density, lb/ft ³	32	D1513
Fines Content, % Bulk shipments Bag shipments	5.0 10.0	D1508
Sieve Residue, ppm No. 325 mesh No. 35 mesh	≤ 50 0	D1514
Heating Loss, % Bulk shipments Bag shipments	1.0 1.0	D1509
Pellet Hardness High Average	60 Max 30 Max	D5230

*Annual Book of ASTM Standards, Vol. 09.01